

# Perlast® G75B

Black multi-purpose high temperature perfluoroelastomer compound

## PERLAST®

### Description

Perlast® G75B offers a unique blend of excellent chemical resistance, mechanical properties and high temperature stability, simultaneously extending the operating limits in all three aspects.

Perlast® G75B has been specially formulated to provide increased acid resistance by eliminating fillers that are prone to acid attack and optimising the polymer structure. In addition, this perfluoroelastomer has low permeability and as a result, it is less prone to swelling, leading to extended in-service performance in, for example, valves, pumps and mechanical seals.

A high modulus makes Perlast® G75B resistant to extrusion and ideal for use in medium-high pressure applications. In addition, the low cumulative compression set provides a high mean-time between maintenance cycles in hot chemically aggressive environments.

Perlast® G75B is suitable for both dynamic and static applications and can be fully moulded into O-rings (any size up to 2m/6.5ft internal diameter) and custom shapes.

### Key Attributes

- ▶ Excellent chemical resistance to a wide range of chemicals
- ▶ Exceptional acid and amine resistance
- ▶ Superior mechanical properties
- ▶ Long-term sealing efficiency at high temperature
- ▶ Extremely low out-gassing properties
- ▶ Good steam resistance (ASME BPE 2000)
- ▶ Less than 2% swell in MIL-L-23699C jet oil after 336 hours at 200°C

### Typical Applications

|                       |  |
|-----------------------|--|
| Aerospace –           | Inter-stage seal assemblies (static O-rings)                                 |
| Chemical Processing – | Pumps<br>Valves<br>Mechanical seals  |
| Diesel –              | Pre-heat chambers<br>Exhaust valve seats                                     |
| Semiconductor –       | Gas abatement systems (static)<br>High temperature environments              |
| Oil & Gas –           | High temperature down-hole environments<br>Electrical bulkhead feed-throughs |

### Other materials in this range

Perlast® G75H (white high temperature up to +320°C/+608°F)  
 Perlast® G75TX (black high temperature up to +327°C/+621°F)  
 Perlast® G75M (black multi-purpose up to +260°C/+500°F)



### Typical Material Properties

| Property   | ASTM  | ISO     | Value                |
|--|-------|---------|----------------------|
| Material Type  | FFKM  | FFPM    |                      |
| Colour   |       |         | Black                |
| Hardness: (°IRHD)<br>(Shore A)                       | D1415 | ISO48   | 78                   |
|  | D2240 | ISO7619 | 79                   |
| Tensile Strength (MPa)                               | D412  | ISO37   | 19.2                 |
| Elongation at break (%)                              | D412  | ISO37   | 160                  |
| 100% Modulus (MPa)                                   | D412  | ISO37   | 12.0                 |
| Compression Set:<br>72 hrs @ 200°C (392°F)           | D395  | ISO815  | 18.0                 |
| Minimum Operating Temperature                        |       |         | -15°C<br>(+5°F)      |
| Maximum Operating Temperature                        |       |         | +325°C<br>(+617°F)   |
| Coefficient of Thermal Expansion (°C <sup>-1</sup> ) |       |         | 4.0x10 <sup>-4</sup> |

**SPECIAL NOTE:** This information is to the best of our knowledge accurate and reliable. However, PPE Ltd makes no warranty, expressed or implied, that parts manufactured from this material will perform satisfactorily in the customer's application. It is the customer's responsibility to evaluate parts prior to use, especially in applications where their failure may result in injury and/or damage. It should also be noted that all elastomeric parts have a finite life, therefore a regular program of inspection and replacement is strongly recommended. The material properties above should not be used for specification purposes.

Perlast® is a registered trademark of Precision Polymer Engineering Limited.



© Copyright Precision Polymer Engineering Ltd | Issue 3, Revision 0

www.prepol.com | Europe: +44 (0) 1254 295400 | USA: +1 408 441 2043 | Asia: +81 804 354 2781 | Email: prepol.sales@idexcorp.com